

Technical Data Sheet

Bioclimatic Cover CB 1500



1: Test Method

2: Units

3: Value

Tensile Strength

MD			TD		
1	ASTM D-882	1	ASTM D-882		
2	MPa	2	MPa		
3	70.0	3	75.0		

Enlogación

MD			TD		
1	ASTM D-882	1	ASTM D-882		
2	%	2	%		
3	5	3	10		

Breaking strength

MD			TD		
1	ASTM D1922	1	ASTM D1922		
2	gr/mm	2	gr/mm		
3	9400	3	15500		

Structural Failures

1	ASTM D-1709		
2	gr.		
3	3200		

Photosynthetic Flux PAR

2	μmol/m2/sec1		
3	1500		

Haze Diffusion Index

2	%		
3	75		

UV Fluxes

2	μmol/m2/sec1		
3	max 30		

Product Lifespan

2	months		
3	36		

Thermicity

2	%		
3	20		

